



# BAYSEAL™ CC X

*Spray-Applied Polyurethane Foam Insulation  
Division 7-Thermal and Moisture Protection*

### Product Description

Bayseal closed-cell X (CC X) spray-applied polyurethane foam insulation is a two component, HFC-245fa blown, medium density, structural system designed for commercial, industrial and residential insulation applications.

Closed-cell polyurethane foam yields a high R-value and may help minimize air and moisture infiltration. This product may also help to control problems associated with moisture vapor drive. The fluid applied, expanding nature of Bayseal CC X foam-forming system during application may also contribute to increased performance value by helping to seal the building envelope.

The Bayseal CC X foam-forming system is comprised of an “A” component or aromatic diisocyanate manufactured by Bayer MaterialScience LLC and a blended “B” component which includes polyols, fire retarding materials, and additives.

Bayseal CC X system has passed the International Code Council Acceptance Criteria 377, for spray-applied polyurethane foam insulation, Appendix X for use without the use of the prescribed ignition barrier and without the need for additional fire resistant coating.

Bayseal CC X foam-forming system is available in two grades for warm and cold weather applications; suggested ambient substrate temperatures are specified below:

System	Substrate/Ambient Temperature
Bayseal CC X	50°F to 120°F
Bayseal CC XP	30°F to 80°F

### Recommended Uses

- |                       |                     |
|-----------------------|---------------------|
| Walls                 | Unvented Attics     |
| Ceilings              | Floors              |
| Vented Attics         | Piping              |
| Unvented Crawl Spaces | Vented Crawl Spaces |
| Foundations           | Concrete Slabs      |
| Ducts                 | Tanks               |
| Cold Storage          | Freezers            |
| Coolers               |                     |

As with any product, use of Bayseal CC X foam-forming system must be tested (including, but not limited to, field testing) in advance by the user to determine suitability.

## Typical Physical Properties\*

Properties	Test Method	Value
Fungi Resistance:	ASTM G-21	Zero Rating
R Value (aged):	ASTM C-518	6.9 at 1 inch 24 at 3.5 inches 38 at 5.5 inches <sup>a</sup> 54 at 7.9 inches <sup>a</sup>
Compressive Strength:	ASTM D-1621	25 psi (nominal)
Core Density:	ASTM D-1622	2.0 lbs./ft <sup>3</sup> (nominal)
Closed Cell Content:	ASTM D-2856	> 90%
Tensile Strength:	ASTM D-1623	60 psi (nominal)
Moisture Vapor Transmission (Permeance):	ASTM E-96	0.80 Perms at 1" 0.23 Perms at 3.5" 0.14 Perms at 5.5" 0.10 Perms at 7.9"
Water Absorption	ASTM D-2842	< 2%
Dimensional Stability: (158°F & 97% R.H.)	ASTM D-2126 % Change in Volume	< 10%
Air Leakage Rate:	ASTM E-2178	< 0.02 L s <sup>-1</sup> m <sup>-1</sup>
Surface Burning Characteristics**	ASTM E-84 4-inches	Flame Spread Index < 25 Smoke Developed Index < 450

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

\*\* These numerical flame spread values are not a true reflection on how this or any material will perform in actual fire conditions.

<sup>a</sup> Values extrapolated from 3.5-inch thick sample testing.

## Environmental Consideration and Substrate Temperatures

Applicators must recognize and anticipate environmental conditions prior to application to ensure the highest quality foam and to maximize yield. Ambient air and substrate temperature, moisture, and wind velocity are all critical determinants of foam quality and selection of the appropriate reactivity formulation. Variations in ambient air and substrate temperature will influence the chemical reaction of the two components, directly affecting the expansion rate, amount of rise, yield, adhesion and the resultant physical properties of the foam insulation.

To obtain optimum results, the Bayseal CC X system should only be spray-applied to substrates when ambient air and surface temperatures fall within the range of 30°F and 120°F. All substrates to be sprayed must be free of dirt, soil, grease, oil and moisture prior to application. Moisture in any form: excessive humidity (>85%R.H.), rain, fog, or ice will react chemically and will adversely affect system performance and corresponding physical properties. Application should not take place when the ambient temperature is within 5°F of the dew point. Primers may be necessary depending upon conditions; consult a Bayer MaterialScience LLC technical service representative.

Wind velocities in excess of 12 miles per hour may result in excessive loss of exotherm and interfere with the mixing efficiency, affecting foam surface, cure, and physical properties and will cause overspray. Precautions must be taken to prevent damage to adjacent areas from overspray.

## Storage Conditions

Store at 70°F to 80°F in a dry and well ventilated area, a minimum of 48 hours prior to application of material. Materials in containers should be maintained at 65°F to 85°F while in use. Conditioned trailers or tanks may be necessary. Material temperature should be confirmed with a thermometer or an infrared gun. Do not configure equipment to recirculate Bayseal CC X system components from proportioner back into drum. Do not recirculate or mix other suppliers' "A" or "B" component into Bayseal CC X system containers.

**CAUTION: If components are below suggested temperatures, the increased viscosity of the components may cause pump cavitation resulting in unacceptable SPF application. If components are above suggested temperatures, there may be loss of blowing agent resulting in diminished yield.**

### Processing Equipment

2:1 transfer pumps are recommended for material transfer from container to the proportioner. The plural component proportioner must be capable of supplying each component within  $\pm 2\%$  of the desired 1:1 mixing ratio by volume. Hose heaters should be set to deliver 120°F to 135°F materials to the spray gun. These settings will ensure thorough mixing in the spray gun mix chamber in typical applications. Optimum hose pressure and temperature will vary with equipment type and condition, ambient and substrate conditions, and the specific application. It is the responsibility of the applicator to properly interpret equipment technical literature, particularly information that relates to the acceptable combinations of gun chamber size, proportioner output, and material pressures. The relationship between proper chamber size and the capacity of the proportioner's pre-heater is critical. Mechanical purge spray guns (specifically direct impingement or DI type) are recommended for highest foam quality.

**CAUTION: Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the "A" and "B" components.**

Processing Parameters and Physical Characteristics	
Pre-heater Temperature:	"A" and "B" 120-135°F
Hose Temperature:	"A" and "B" 120-135°F
Pressures:	1000-1500 psi (dynamic)*
Mix Ratio Parts:	1 to 1 by volume "A" to "B"
Viscosity at 75°F	400-500 cps "B" Component
Shelf Life	6 months @ 65°F to 80°F

\* Dependent upon hose length.

### Thermal Barrier

The International Building Code and International Residential Code require that SPF be separated from the interior of a building by an approved fifteen (15) minute thermal barrier, such as 1/2" gypsum wall board or equivalent, installed per manufacturer's instructions and corresponding code requirements. The International Building Code allows for omission of the prescribed thermal barrier in certain instance, such as:

- attics and crawlspaces with limited access
- approval by way of diversified testing, such as room corner protocols

Local building codes may vary and must be consulted for applicability of thermal barrier exceptions.

### Handling Information

Applicators should ensure the safety of the jobsite and construction personnel by posting appropriate signs warning that all "hot work" such as welding, soldering, and cutting with torches should not take place until a thermal barrier or approved equivalent is installed over any exposed polyurethane foam.

### Vapor Retarder

Bayseal CC X system qualifies as a vapor retarder as defined by the International Code Council and ASHRAE (Class II) at a minimum thickness of one inch. Building construction types with a persistent, high moisture drive require additional moisture remediation. The contractor should consult local building codes to establish the vapor retarder requirement.

### **Per Lift Application**

Applicators should limit per lift thickness of foam made with the Bayseal CC X system to 2 inches for optimal processing and physical properties, with the following exception: If the lift encapsulates CPVC piping the maximum lift thickness is 2 inches. Second lifts, if necessary, should be applied after 10 minutes of cure time. For substrates with special sensitivity to heat, the resultant exotherm must be considered before application of SPF. It is the responsibility of the applicator to ensure SPF exotherm will not adversely affect substrates.

### **Health and Safety Information**

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling materials used to produce foam made with the Bayseal CC X system. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets, product labels, and safe use and handling guidelines. More resources are available at [spraypolyurethane.com](http://spraypolyurethane.com), [polyurethane.org](http://polyurethane.org), [sprayfoam.org](http://sprayfoam.org), [baycareonline.com](http://baycareonline.com), or by contacting the Bayer MaterialScience Product Safety and Regulatory Affairs Department in Pittsburgh, PA.

Note: The information contained in this bulletin is current as of September 2011, please contact Bayer MaterialScience to determine whether this publication has been revised.

### **Bayer MaterialScience LLC**

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-800-662-2927 • [www.spf.bayermaterialscience.com](http://www.spf.bayermaterialscience.com)

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

---

### **Sales Offices**

---

2400 Spring Steubner Road West, Spring, TX 77389 • 1-800-221-3626 • Fax: 1-281-288-6450

---